

U.S. Patent Application of BEASE et al., Appln. No. 10/644,957

IN THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Previously Presented) A method of processing a layer containing a high-permittivity material in a plasma processing system, the method comprising:  
providing a layer containing a high-permittivity material overlying a substrate, wherein the high-permittivity material is substantially free of Si;  
modifying the layer containing the high-permittivity material by exposing the layer to a plasma; and  
wet etching to remove the modified layer containing the high-permittivity material.
2. (Original) The method as claimed in claim 1, wherein the modifying partially removes the layer containing the high-permittivity material.
3. (Previously Presented) The method as claimed in claim 1, wherein the modifying disrupts the atomic structure of the layer containing the high-permittivity material.
4. (Original) The method according to claim 1, wherein the modifying comprises introducing a process gas into a plasma chamber and creating the plasma, the process gas comprising a reactive gas.

U.S. Patent Application of BEASE et al., Appln. No. 10/644,957

5. (Original) The method according to claim 4, wherein the reactive gas comprises at least one of HBr and HCl.
6. (Original) The method according to claim 4, wherein the process gas further comprises an inert gas.
7. (Original) The method according to claim 6, wherein the inert gas is selected from He, Ne, Ar, Kr, Xe, or mixtures thereof.
8. (Original) The method according to claim 1, wherein the modifying comprises introducing a process gas into a plasma chamber and creating the plasma, the process gas comprising an inert gas.
9. (Original) The method according to claim 8, wherein the inert gas is selected from He, Ne, Ar, Kr, Xe, or mixtures thereof.
10. (Previously Presented) The method according to claim 1, wherein the high-permittivity material comprises at least one of Ta<sub>2</sub>O<sub>5</sub>, TiO<sub>2</sub>, ZrO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, and HfO<sub>2</sub>.
11. (Original) The method according to claim 1, wherein the modifying further comprises RF powering a substrate holder that exposes the substrate containing the high-permittivity material to the plasma.

U.S. Patent Application of BEASE et al., Appln. No. 10/644,957

12. (Original) The method according to claim 1, wherein the modifying further comprises grounding a substrate holder that exposes the substrate containing the high-permittivity material to the plasma.

13. (Original) The method according to claim 1, wherein the modifying further comprises applying a DC bias to a substrate holder that exposes the substrate containing the high-permittivity material to the plasma.

14. (Original) The method according to claim 1, wherein the modifying further comprises electrically isolating a substrate holder from the plasma processing system, the substrate holder exposing the substrate containing the high-permittivity material to the plasma.

15. (Previously Presented) A method of processing a layer containing a high-permittivity material in a plasma processing system, the method comprising:  
providing a layer containing a high-permittivity material overlying a substrate, wherein the high-permittivity material is substantially free of Si;  
introducing a process gas into a plasma processing chamber and creating a plasma;  
modifying the layer containing the high-permittivity material by exposing the layer to the plasma; and  
removing the modified layer containing the high-permittivity material using wet etching.

U.S. Patent Application of BEASE et al., Appln. No. 10/644,957

16. (Previously Presented) A method of processing a layer containing a high-permittivity material in a plasma processing system, the method comprising:  
providing a layer containing a high-permittivity material overlying a substrate, wherein the high-permittivity material is substantially free of Si;  
introducing a process gas into a plasma processing chamber and creating a plasma;  
anisotropically modifying the layer containing the high-permittivity material in accordance with a pattern by exposing the layer to the plasma; and  
removing the layer containing a high-permittivity material using wet etching.

17. (Withdrawn) A plasma processing system comprising:  
a process chamber capable of sustaining a plasma;  
a gas injection system configured to inject a process gas into the process chamber;  
a plasma source configured to create plasma from said process gas;  
a substrate holder that exposes a substrate comprising a layer of high-permittivity materials to the plasma, thereby modifying the layer;  
a controller that controls the plasma processing system; and  
a wet cleaning chamber disposed in or operatively coupled to said process chamber.

18. (Withdrawn) The system according to claim 17, wherein the plasma source comprises an inductive coil.

**U.S. Patent Application of BEASE et al., Appln. No. 10/644,957**

19. (Withdrawn) The system according to claim 17, wherein the plasma source comprises a plate electrode.
20. (Withdrawn) The system according to claim 17, wherein the plasma source comprises an antenna.
21. (Withdrawn) The system according to claim 17, wherein the plasma source comprises an ECR source.
22. (Withdrawn) The system according to claim 17, wherein the plasma source comprises a Helicon wave source.
23. (Withdrawn) The system according to claim 17, wherein the plasma source comprises a surface wave source.
24. (Withdrawn) The system according to claim 17, wherein the process gas comprises a reactive gas.
25. (Withdrawn) The system according to claim 24, wherein the reactive gas comprises at least one of HBr and HCl.
26. (Withdrawn) The system according to claim 24, wherein the process gas further comprises an inert gas.

## U.S. Patent Application of BEASE et al., Appln. No. 10/644,957

27. (Withdrawn) The system according to claim 26, wherein the inert gas is selected from He, Ne, Ar, Kr, Xe, or mixtures thereof.
28. (Withdrawn) The system according to claim 17, wherein the process gas comprises an inert gas.
29. (Withdrawn) The system according to claim 28, wherein the inert gas is selected from He, Ne, Ar, Kr, Xe, or mixtures thereof.
30. (Withdrawn) The system according to claim 17, wherein the high-permittivity material comprises at least one of Ta<sub>2</sub>O<sub>5</sub>, TiO<sub>2</sub>, ZrO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, HfSiO, and HfO<sub>2</sub>.
31. (Withdrawn) The system according to claim 17, wherein said wet cleaning chamber is operatively coupled to said process chamber.
32. (Withdrawn) The system according to claim 17, wherein said wet cleaning chamber is disposed in said process chamber.
33. (Withdrawn) The system according to claim 17, wherein the substrate holder is RF powered.
34. (Withdrawn) The system according to claim 17, wherein the substrate holder is grounded.

U.S. Patent Application of BEASE et al., Appln. No. 10/644,957

35. (Withdrawn) The system according to claim 17, wherein a DC bias is applied to the substrate holder.

36. (Withdrawn) The system according to claim 17, wherein the substrate holder is electrically isolated from the plasma processing system.

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**